

TAUBMANS PAINTS WATER BASED ENAMEL

AUSTRALIAN COATING GUIDELINES FOR DURAMAX DOORS

Taubmans 3 in1 Prep & Taubmans Water Based Enamel

Taubmans has been built on technical superiority and delivers quality proven results across many business units including the architectural segment. With a 700-strong research and development team, PPG keeps this proud tradition alive. We're constantly introducing revolutionary new technologies like Microban®, and Nanoguard® with its unique, interlocking molecular structure.

Coating System Summary: Duramax Composite Doors

Taubmans Water based enamel (Available in Low Sheen, Semi- Gloss and Gloss)

1 st Coat:	Taubmans Paints 3 in 1 Prep
2 nd Coat:	Taubmans Water Based Enamel
3 rd Coat:	Taubmans Water Based Enamel
Spread Rate:	Up to 12m ² /L per coat (Taubmans 3 in 1 Prep). Up to 16m ² /L per coat (Taubmans Water Based Enamel).
Recoat Time:	2 hours
Dry Film Thickness	25-30 microns per coat

SURFACE PREPARATION

1. Thoroughly wash all surfaces with liquid sugar soap. Rinse with clean water and allow to dry.
2. Important: Scuff sand with 120-240 grit sandpaper or medium sanding block. Missing this step will mean the finish is unlikely to adhere.
3. Dust down surface, until it is dust free.
4. Lay door horizontally for painting where possible.



Taubmans 3 in 1 prep application:

1. Stir Taubmans 3 in 1 using a broad paddle stirrer prior to use until the paint is thoroughly mixed including any tint within the paint.
2. Apply 1 coat of Taubmans 3 in 1 prep and allow to completely dry ensuring 2 hours prior to over coating with topcoat.



Taubmans Water Based Enamel Application:

3. Stir Taubmans Water Based Enamel using a broad paddle stirrer prior to use until the paint is thoroughly mixed including any tint within the paint.
4. Apply 2 coats of Taubmans Water Based Enamel using a brush, roller or spray gun. * In coastal areas a 3rd coat is recommended due to harsh salt atmospheric conditions.
5. Taubmans Water Based Enamel will be touch dry in 30 minutes. Allow 2 hours for recoat at 25 deg C and allow 4 hours in cold or humid conditions. Do not use below 10 deg C above 35 deg C or when humidity is excessive or if rain showers or dew is expected within 6 hours of application.

CARE & MAINTENANCE

Protect the coating from abrasive contact for at least 5 days.

Even a well-finished fiberglass or composite door will be affected by exposure and UV weathering from sun, moisture, and air pollutants. It is considered normal to undergo maintenance when the surface begins to deteriorate and the sheen level of the coating reduces.

Periodically cleaning the surface of your painted Duramax door with a mix of water and mild detergent solution will remove contaminants which can erode and damage the coating system over time especially in coastal areas. Simple maintenance cleaning will extend the service life of the coating and ensure better longevity. It is important to recoat the surface when the coating begins to show signs of wear. Simply wash down with a mild detergent and water solution, rinse off and allow to dry. Apply a refresher coat of Taubmans Water Based Enamel in your preferred colour following instructions of back of pack.

Monitoring the surface every 2 years is recommended and maintenance schedules vary for every project and location.

parkwooddoors.com.au 1800 681 586

taubmans.com.au 131 686